Amendments to the claims:

The following claim listing replaces all previous claim listings in the application.

- (Currently amended) A process for preparing a moisture-curable, polyether urethane containing terminal cyclic urea/reactive silane groups which comprises reacting at an NCO:OH equivalent ratio of 1.5:1 to 2.5:1
- a) a hydroxyl component containing
 - i) 20 to 100% by weight, based on the weight of component a), of a polyether containing two hydroxyl groups and one or more polyether segments, wherein the polyether segments have a number average molecular weight of at least 30006,000 and a degree of unsaturation of less than 0.04 milliequivalents/g, provided that the sum of the number average molecular weights of all of the polyether segments per molecule averages 6000 to 20,000, and
 - ii) 0 to 80% by weight, based on the weight of component a), of a polyether containing one hydroxyl group and one or more polyether segments having a number average molecular weight of 1000 to 15,000,3,000 to 12,000 with
- b) an isocyanate component containing
 - 20 to 100% by weight, based on the weight of component b), of a compound containing two isocyanate groups, and
 - 0 to 80% by weight, based on the weight of component b), of a compound containing one isocyanate group.

provided that total percentages of a-ii) and b-ii) add up to at least 10, to form an isocyanate-containing reaction product and subsequently reacting this reaction product at an equivalent ratio of isocyanate groups to isocyanate-reactive groups of 0.8:1 to 1.1:1 with

 a compound containing an isocyanate-reactive group and one reactive silane groups in which at least 10 mole % of component c) is a compound corresponding to the formula

- X represents identical or different organic groups which are inert to isocyanate groups below 100°C, provided that at least two of these groups are alkoxy or acyloxy groups,
- Y represents a linear or branched alkylene group containing 1 to 8 carbon atoms,
- R_1 and R_2 are identical or different and represent organic groups which are inert to isocyanate groups at a temperature of 100°C or less and
- R₃ and R₄ are identical or different and represent hydrogen or organic groups which are inert towards isocyanate groups at a temperature of 100°C or less,

to form an intermediate polyether urethane containing at least a portion of terminal non-cyclic urea/reactive silane groups corresponding to formula II

and converting the non-cyclic urea groups to cyclic urea groups by reacting the intermediate polyether urethane in the presence of an acid catalyst and heat to form terminal cyclic urea/reactive silane groups corresponding to formula III

and/or formula IV

Formula III

Formula IV

- 2. (Original) The process of Claim 1 wherein at least 50 mole % of component c) is a compound corresponding to formula I.
- 3. (Original) The process of Claim 1 wherein at least 80 mole % of component c) is a compound corresponding to formula I and
- X represents identical or different alkoxy groups having 1 to 4 carbon atoms,
- Y represents a linear radical containing 2 to 4 carbon atoms or a branched radical containing 5 to 6 carbon atoms and

R₁ and R₂ are identical or different and represent alkyl groups having

1 to 4 carbon atoms and

R₃ and R₄ represent hydrogen.

- 4. (Original) The process of Claim 1 wherein component a-i) is present in an amount of 20 to 90% by weight, based on the weight of component a); and component a-ii) is present in an amount of 10 to 80% by weight, based on the weight of component a).
- 5. (Original) The process of Claim 2 wherein component a-i) is present in an amount of 20 to 90% by weight, based on the weight of component a); and component a-ii) is present in an amount of 10 to 80% by weight, based on the weight of component a).

- 6. (Original) The process of Claim 3 wherein component a-i) is present in an amount of 20 to 90% by weight, based on the weight of component a); and component a-ii) is present in an amount of 10 to 80% by weight, based on the weight of component a).
- 7. (Original) The process of Claim 1 wherein component b-i) is present in an amount of 20 to 90% by weight, based on the weight of component b); and component b-ii) is present in an amount of 10 to 80% by weight, based on the weight of component b).
- 8. (Original) The process of Claim 2 wherein component b-i) is present in an amount of 20 to 90% by weight, based on the weight of component b); and component b-ii) is present in an amount of 10 to 80% by weight, based on the weight of component b).
- 9. (Original) The process of Claim 3 wherein component b-i) is present in an amount of 20 to 90% by weight, based on the weight of component b); and component b-ii) is present in an amount of 10 to 80% by weight, based on the weight of component b).
- 10. (Original) The process of Claim 1 wherein component a-i) is present in an amount of 30 to 80% by weight, based on the weight of component a); component a-ii) is present in an amount of 20 to 70% by weight, based on the weight of component a).
- 11. (Original) The process of Claim 2 wherein component a-i) is present in an amount of 30 to 80% by weight, based on the weight of component a); component a-ii) is present in an amount of 20 to 70% by weight, based on the weight of component a).
- 12. (Original) The process of Claim 3 wherein component a-i) is present in an amount of 30 to 80% by weight, based on the weight of component a); PO-7632US 6 -

component a-ii) is present in an amount of 20 to 70% by weight, based on the weight of component a).

- 13. (Original) The process of Claim 1 wherein component b-i) is present in an amount of 30 to 80% by weight, based on the weight of component b); component b-ii) is present in an amount of 20 to 70% by weight, based on the weight of component b).
- 14. (Original) The process of Claim 2 wherein component b-i) is present in an amount of 30 to 80% by weight, based on the weight of component b); component b-ii) is present in an amount of 20 to 70% by weight, based on the weight of component b).
- 15. (Original) The process of Claim 3 wherein component b-i) is present in an amount of 30 to 80% by weight, based on the weight of component b); component b-ii) is present in an amount of 20 to 70% by weight, based on the weight of component b).
 - 16 20 (Canceled)